

Product Texts

General purpose grade for any technical or aesthetic use.

Flammability @3.2mm nom. thickn. V-2 -
 Flammability @1.6mm nom. thickn. V-2 -

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3200 / -	MPa	ISO 527
^[C] Charpy impact strength, +23°C	40 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	170 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	8.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	- / 1160	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black

Applications

General Purpose