

GLAMIDE® T-808-02

PA6

Toyobo Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	40	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	75 / 40	MPa	ASTM D 638
Compressive Strength	80 / -	MPa	ASTM D 695
Flexural Modulus	3300 / 1300	MPa	ASTM D 790
Flexural Strength	100 / 45	MPa	ASTM D 790
Rockwell Hardness	R 120 /	-	ASTM D 785
Izod Impact notched, 1/8 in	43 / 175	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	30 / 45	J/m	ASTM D 256
Temperature	-40	°C	-
Thermal properties			
	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696
DTUL @ 66 psi	190	°C	ASTM D 648
DTUL @ 264 psi	84	°C	ASTM D 648
Electrical properties			
	dry / cond	Unit	Test Standard
ISO Data			
Comparative tracking index	600 / 600	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	25 / 17	kV/mm	ASTM D 149
Volume Resistivity	1E15 / 1E12	Ohm*cm	ASTM D 257
Arc Resistance	120 / 105	s	ASTM D 495
Other properties			
	Value	Unit	Test Standard
Water Absorption, 24hr	1.3	%	ASTM D 570
Water Absorption, Equilibrium	3	%	ASTM D 570
Density	1180	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	3 - 5	h	-
Melt temperature	240 - 260	°C	-
Mold temperature	80	°C	-
Injection pressure	30 - 45	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Flame retardant, Halogen-free