

| Mechanical properties | Value | Unit | Test Standard |
|-------------------------------|-------|-------------------|---------------|
| ISO Data | | | |
| Tensile Modulus | 14400 | MPa | ISO 527 |
| Stress at break | 95 | MPa | ISO 527 |
| Strain at break | 1.4 | % | ISO 527 |
| Charpy impact strength, +23°C | 22.9 | kJ/m ² | ISO 179/1eU |

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|-------|------|----------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 220 | °C | ISO 11357-1/-3 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 2240 | kg/m ³ | ISO 1183 |

Characteristics

Processing

Injection Molding

Special Characteristics

Thermally Conductive

Applications

Automotive, Encapsulation

Regional Availability

Europe