

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	63	MPa	ISO 527
Strain at break	35	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Charpy notched impact strength, +23°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	R112	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.4	-	IEC 62631-2-1

Other properties	Value	Unit	Test Standard
Humidity absorption	1.5	%	Sim. to ISO 62
Density	1110	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.05	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	240	°C	-
Zone 2	250	°C	-
Zone 3	250	°C	-
Nozzle temperature	250	°C	-
Screw speed	80 - 120	rpm	-
Back pressure	0.5 - 1	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific