

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	40	MPa	ISO 527
Strain at break	80	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	50	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, B	170	°C	ISO 306
Electrical properties			
ASTM Data			
Surface Resistivity	1E8	Ohm	ASTM D 257
Other properties			
Density	1120	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	60 - 70	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

High impact or impact modified