

NEVIFLAM PA6 160 HF

PA6

Nevicolor S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Flexural modulus, 23°C	3000	MPa	ISO 178
Izod notched impact strength, +23°C	3.5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, A	210	°C	ISO 306
Vicat softening temperature, B	195	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
Density	1180	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant

Regional Availability

Europe