

Product Texts

Extrusion, Film Extrusion, Food Contact Quality, Antiblock, Lubricated

ISO 1043 PA6

| Thermal properties | dry / cond | Unit | Test Standard |
|--|------------|------|----------------|
| ISO Data | | | |
| ^[C] Melting temperature, 10°C/min | 220 / * | °C | ISO 11357-1/-3 |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|------------------------------------|------------|-------------------|----------------|
| ^[C] Humidity absorption | 2.8 / * | % | Sim. to ISO 62 |
| ^[C] Density | 1130 / - | kg/m ³ | ISO 1183 |

[C]: CAMPUS

| Material specific properties | dry / cond | Unit | Test Standard |
|---------------------------------|------------|--------------------|---------------------|
| ISO Data | | | |
| ^[C] Viscosity number | 194 / * | cm ³ /g | ISO 307, 1157, 1628 |

[C]: CAMPUS

Characteristics**Processing**

Film Extrusion

Additives

Lubricants, Antiblocking agent

Delivery form

Pellets

Regional Availability

Asia Pacific