

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® LW9320 NC010 is a 20% glass fiber reinforced polybutylene terephthalate blend for injection molding. It has improved surface aesthetics, excellent dimensional stability and low warpage characteristics.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	5	kg	-
^[C] Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
^[C] Density of melt	1170	kg/m ³	-
^[C] Thermal conductivity of melt	0.24	W/(m K)	-
^[C] Spec. heat capacity of melt	1900	J/(kg K)	-
^[C] Ejection temperature	170	°C	-
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

^[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	7500	MPa	ISO 527
^[C] Stress at break	120	MPa	ISO 527
^[C] Strain at break	2.5	%	ISO 527
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	45	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	8.5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	7000	MPa	ASTM D 638
Tensile Strength	110	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	6000	MPa	ASTM D 790
Flexural Strength	155	MPa	ASTM D 790
Izod Impact notched, 1/8 in	86	J/m	ASTM D 256

^[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	110	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	175	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

Crastin® LW9320 NC010

(PBT+SAN)-I-GF20

Celanese

^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	31	mm/min	ISO 3795 (FMVSS 302)
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
DTUL @ 66 psi	213	°C	ASTM D 648
DTUL @ 264 psi	178	°C	ASTM D 648
Melting Temperature	225	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	500	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	23	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.013	-	ASTM D 150
Dielectric Constant, 1 MHz	3.2	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.3	%	Sim. to ISO 62
^[C] Density	1340	kg/m ³	ISO 1183
Density	1350	kg/m ³	ASTM D 792

[C]: CAMPUS

Material specific properties	Value	Unit	Test Standard
ISO Data			
^[C] Viscosity number	120	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Special Characteristics

High impact or impact modified

Features

Low Warpage, Weldable

Chemical Resistance

General Chemical Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa