

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® LW9330 BK851 is a 30% glass fiber reinforced polybutylene terephthalate blend for injection molding. It has improved surface aesthetics, excellent dimensional stability and low warpage characteristics.

Processing/Physical Characteristics	Value	Unit	Test Standard
-------------------------------------	-------	------	---------------

ISO Data

^[C] Ejection temperature	170	°C	-
-------------------------------------	-----	----	---

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
-----------------------	-------	------	---------------

ISO Data

^[C] Tensile Modulus	9600	MPa	ISO 527
--------------------------------	------	-----	---------

^[C] Stress at break	133	MPa	ISO 527
--------------------------------	-----	-----	---------

^[C] Strain at break	2.2	%	ISO 527
--------------------------------	-----	---	---------

^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
--	----	-------------------	-------------

^[C] Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
--	---	-------------------	-------------

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
--------------------	-------	------	---------------

ISO Data

^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
--	-----	----	----------------

^[C] Glass transition temperature, 10°C/min	110	°C	ISO 11357-1/-2
---	-----	----	----------------

^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
--	----	-------	-----------------

Thickness tested	1.5	mm	-
------------------	-----	----	---

Yellow Card available	yes	-	-
-----------------------	-----	---	---

^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
--	----	-------	-----------------

Thickness tested	0.8	mm	-
------------------	-----	----	---

Yellow Card available	yes	-	-
-----------------------	-----	---	---

^[C] Burning rate, FMVSS, Thickness 1 mm	32	mm/min	ISO 3795 (FMVSS 302)
--	----	--------	----------------------

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
------------------	-------	------	---------------

^[C] Density	1420	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Low Warpage

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America

Special Characteristics

High impact or impact modified