Crastin® LW9330 NC010

(PBT+SAN)-I-GF30 Celanese

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.
If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® LW9330 NC010 is a 30% glass fiber reinforced polybutylene terephthalate blend for injection molding. It has improved surface aesthetics, excellent dimensional stability and low warpage characteristics.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
[C] Melt volume-flow rate, MVR	**10**	cm³/10min	ISO 1133
Temperature	**250**	°C	-
Load	**5**	kg	-
[C] Molding shrinkage, parallel	**0.3**	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**0.6**	%	ISO 294-4, 2577
[C] Density of melt	**1270**	kg/m³	-
[C] Thermal conductivity of melt	**0.28**	W/(m K)	-
[C] Spec. heat capacity of melt	**1790**	J/(kg K)	-
[C] Ejection temperature	**170**	°C	-
ASTM Data			
Mold Shrinkage, MD	**0.002**	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**9800**	MPa	ISO 527
[C] Stress at break	**135**	MPa	ISO 527
[C] Strain at break	**2.3**	%	ISO 527
[C] Charpy impact strength, +23°C	**55**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**9**	kJ/m²	ISO 179/1eA
[C] Charpy notched impact strength, -30°C	**9**	kJ/m²	ISO 179/1eA
ASTM Data			
Tensile Modulus	**9000**	MPa	ASTM D 638
Tensile Strength	**131**	MPa	ASTM D 638
Elongation at Break	**2**	%	ASTM D 638
Flexural Modulus	**8275**	MPa	ASTM D 790
Flexural Strength	**179**	MPa	ASTM D 790
Izod Impact notched, 1/8 in	**96**	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	**96**	J/m	ASTM D 256
Temperature	**-40**	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Melting temperature, 10°C/min	**225**	°C	ISO 11357-1/-3
[C] Glass transition temperature, 10°C/min	**110**	°C	ISO 11357-1/-2
[C] Temp. of deflection under load, 1.80 MPa	**185**	°C	ISO 75-1/-2
[C] Coeff. of linear therm. expansion, parallel	**25**	E-6/K	ISO 11359-1/-2
[C] Coeff. of linear therm. expansion, normal	**125**	E-6/K	ISO 11359-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	**HB**	class	IEC 60695-11-10
Thickness tested	**1.5**	mm	-

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

Yellow Card available	**yes**	-	-
[C] Burning Behav. at thickness h	**HB**	class	IEC 60695-11-10
Thickness tested	**0.8**	mm	-
Yellow Card available	**yes**	-	-
[C] Burning rate, FMVSS, Thickness 1 mm	**28**	mm/min	ISO 3795 (FMVSS 302)
ASTM Data			
UL 94 Flame rating	**HB**	-	UL 94
Thickness tested	**0.75**	mm	-
DTUL @ 66 psi	**215**	°C	ASTM D 648
DTUL @ 264 psi	**190**	°C	ASTM D 648
Melting Temperature	**225**	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
[C] Surface resistivity	**>1E15**	Ohm	IEC 62631-3-2
[C] Comparative tracking index	**550**	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	**23**	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	**0.013**	-	ASTM D 150
Dielectric Constant, 1 MHz	**3.4**	-	ASTM D 150
Surface Resistivity	**>1E15**	Ohm	ASTM D 257
Volume Resistivity	**>1E15**	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Water absorption	**1**	%	Sim. to ISO 62
[C] Humidity absorption	**0.25**	%	Sim. to ISO 62
[C] Density	**1420**	kg/m³	ISO 1183
Density	**1430**	kg/m³	ASTM D 792

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Delivery form
Pellets, Natural Color

Additives
Lubricants, Release agent

Special Characteristics
High impact or impact modified

Features
Low Warpage

Chemical Resistance
General Chemical Resistance

Applications
Automotive

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.