

NYLENE 323 HS

PA6

Polymeric Resources Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	55.2	MPa	ASTM D 638
Flexural Modulus	517.1	MPa	ASTM D 790
Izod Impact notched, 1/8 in	534	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	55	°C	ASTM D 648
Melting Temperature	210	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	66 - 82	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.2	%	-
Melt temperature	249 - 282	°C	-
Mold temperature	49 - 93	°C	-
Zone 1	227 - 260	°C	-
Zone 2	238 - 271	°C	-
Zone 3	249 - 282	°C	-
Nozzle temperature	249 - 282	°C	-
Injection pressure	7 - 15	MPa	-
Back pressure	0 - 50	MPa	-
Holding pressure	5 - 12	MPa	-

Characteristics**Processing**

Injection Molding, Pipe/Tube Extrusion, Profile Extrusion

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Copolymer

Chemical Resistance

General Chemical Resistance

Applications

Automotive

Regional Availability

North America