

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>2792</b>	MPa	ASTM D 638
Tensile Strength	<b>71</b>	MPa	ASTM D 638
Flexural Modulus	<b>2351</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>80.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>216</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1130</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>66 - 82</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.2</b>	%	-
Melt temperature	<b>238 - 271</b>	°C	-
Mold temperature	<b>49 - 93</b>	°C	-
Zone 1	<b>221 - 249</b>	°C	-
Zone 2	<b>227 - 260</b>	°C	-
Zone 3	<b>328 - 271</b>	°C	-
Nozzle temperature	<b>238 - 271</b>	°C	-
Injection pressure	<b>4 - 12</b>	MPa	-
Back pressure	<b>0 - 50</b>	MPa	-
Holding pressure	<b>3 - 9</b>	MPa	-
Maximum residence time	<b>6</b>	min	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Applications**

Automotive, General Purpose

**Regional Availability**

North America