

Product Texts

Product-nomenclature: ISO 16396-PA6T/6I,GF40,M1H,C12-140

Product Attributes

Hydrolysis resistant

Markets**Automotive**

Air intake systems, Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Cooling and climate control, Fuel systems, Powertrain and Chassis, Interior, Exterior

Approvals**Food Contact**

NSF 51, EU Requirements, FDA

Potable Water Contact

NSF 61, KTW, WRAS, ACS, DVGW W270

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14500 / 14500	MPa	ISO 527
^[C] Stress at break	250 / 230	MPa	ISO 527
^[C] Strain at break	2 / 2	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / 70	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	65 / 65	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11 / 11	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11 / 11	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	325 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	280 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	200 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	15 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	45 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E10 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
^[C] Electric strength	30 / 30	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	3.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.5 / *	%	Sim. to ISO 62
^[C] Density	1530 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Granules, Black

Chemical Resistance

Hydrolytically Stable

Certifications

Food contact, Food approval FDA 21 CFR, Food approval NSF 51, Drinking water contact, Drinking water contact KTW, Drinking water contact DVGW W270, Drinking water contact NSF 61

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa