

Product Texts

Standard type with medium viscosity partly aromatic Polyamid with 40% glass fiber content and heat stabilized.
For all kind of injection mloading parts with high stiffness at exellent thermal stability and low moisture absorption.

preliminary data

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	14500 / 14000	MPa	ISO 527
Stress at break	220 / 210	MPa	ISO 527
Strain at break	2 / 2	%	ISO 527
Charpy impact strength, +23°C	70 / 70	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8 / 8	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	330 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	280 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	290 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Electric strength	30 / -	kV/mm	IEC 60243-1
Comparative tracking index	550 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	3.3 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1530 / -	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Regional Availability

Europe