

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	194	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	10	%	ASTM D 570
Density	1120	kg/m ³	ASTM D 792
Moisture Content	0.8	%	-
Bulk Density	670	kg/m ³	-

Characteristics

Processing

Blown Film Extrusion, Film Extrusion, Thermoforming

Delivery form

Pellets

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Features

Copolymer

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR, Food contact notification (FCN)

Applications

Packaging

Regional Availability

North America