

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>194</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, Equilibrium	<b>10</b>	%	ASTM D 570
Density	<b>1120</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.8</b>	%	-
Bulk Density	<b>670</b>	kg/m <sup>3</sup>	-

**Characteristics**

**Processing**

Blown Film Extrusion, Film Extrusion, Thermoforming

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Copolymer

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR, Food contact notification (FCN)

**Applications**

Packaging

**Regional Availability**

North America