

Amilan® CM8000

PA*

Toray Industries, Inc.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	21	MPa	ISO 527
Strain at break	25	%	ISO 527

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	137	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ISO 1183

Characteristics**Features**

Copolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa