

4LOY 10E17400

(PC+ABS)

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2150	MPa	ISO 527
Stress at break	48	MPa	ISO 527
Strain at break	50	%	ISO 527
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Izod notched impact strength	35	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	112	°C	ISO 75-1/-2
Vicat softening temperature, B	114	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
Density	1100	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Regional Availability

Europe