

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	7	MPa	ISO 527
Strain at break	460	%	ISO 527
Shore D hardness	35	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	980	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Feed temperature	150 - 170	°C	-
Zone 1	175 - 190	°C	-
Zone 2	200 - 210	°C	-
Zone 3	210 - 220	°C	-
Nozzle temperature	230 - 250	°C	-

Characteristics**Processing**

Other Extrusion

Certifications

Contains renewable resources

Features

Copolymer

Applications

Automotive

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa