

PlusTek PB892WT168

PA6

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1950	MPa	ISO 527
Tensile Strength	44	MPa	ISO 527
Yield strain	4.2	%	ISO 527
Izod notched impact strength, +23°C	46	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	46 -40	kJ/m ² °C	ISO 180/1A -
ASTM Data			
Izod Impact notched, 1/8 in	660	J/m	ASTM D 256
Izod Impact notched, Low-Temperature Temperature	610 -40	J/m °C	ASTM D 256 -
Other properties			
Water absorption	9	%	Sim. to ISO 62
Humidity absorption	3	%	Sim. to ISO 62
Density	1060	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.15	%	-
Mold temperature	55 - 90	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	230 - 240	°C	-
Zone 2	230 - 240	°C	-
Zone 3	230 - 270	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

White

Special Characteristics

High impact or impact modified

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa