

**PlusTek PB902NT**

PA6

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2900	MPa	ISO 527
Tensile Strength	80	MPa	ISO 527
Yield strain	3.9	%	ISO 527
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Water absorption	9	%	Sim. to ISO 62
Humidity absorption	3	%	Sim. to ISO 62
Density	1130	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-

**Characteristics****Processing**

Wire/Cable Extrusion, Coating

**Delivery form**

Natural Color

**Features**

High Coefficient of Friction

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa