

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	5	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	42	MPa	ISO 527
<b>ASTM Data</b>			
Flexural Modulus	2200	MPa	ASTM D 790
Izod Impact notched, 1/8 in	250	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	3.2	mm	-
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	>1E15	Ohm	ASTM D 257
<b>Other properties</b>			
Density	1110	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Granules, Black

#### Certifications

Recycled Resin Content

#### Applications

Packaging

#### Regional Availability

Europe