RAVAMID® B T BK

PA6 Ravago Group

Product Texts

Polyamide 6 black containing recycled material, impact modified, also available UV Stabilized (UV).

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	**1.0**	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	**50**	MPa	ISO 527
Stress at break	**45**	MPa	ISO 527
Strain at break	**20**	%	ISO 527
Flexural modulus, 23°C	**2000**	MPa	ISO 178
Charpy notched impact strength, +23°C	**9**	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	**8**	kJ/m²	ISO 179/1eA
Izod notched impact strength, +23°C	**10**	kJ/m²	ISO 180/1A
Izod notched impact strength	**8**	kJ/m²	ISO 180/1A
Temperature	**-23**	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**50**	°C	ISO 75-1/-2
Vicat softening temperature, B	**195**	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	**HB**	class	IEC 60695-11-10
Thickness tested	**1.6**	mm	-
Burning behav. at thickness h	**HB**	class	IEC 60695-11-10
Thickness tested	**3.2**	mm	-
Glow Wire Flammability Index (GWFI)	**650**	°C	IEC 60695-2-12
GWFI - thickness tested (1)	**2**	mm	-

Other properties	Value	Unit	Test Standard
Humidity absorption	**0.25**	%	Sim. to ISO 62
Density	**1080**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**75**	°C	-
Pre-drying - Time	**3 - 4**	h	-
Processing humidity	**≤0.12**	%	-
Melt temperature	**240 - 270**	°C	-
Mold temperature	**70 - 90**	°C	-
Zone 1	**220 - 230**	°C	-
Zone 2	**230 - 245**	°C	-
Zone 3	**250 - 260**	°C	-
Nozzle temperature	**250 - 260**	°C	-
Screw speed	**50 - 80**	rpm	-
Back pressure	**0.4 - 0.8**	MPa	-
Holding pressure	**6 - 8**	MPa	-

Characteristics

Processing
Injection Molding

Certifications
Recycled Resin Content

Delivery form
Black

Regional Availability
Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.