

RESTRAMID B27 MI 9003 1A0000

PA6

Polimarky Spółka Jawna

| Mechanical properties | dry / cond | Unit | Test Standard |
|-------------------------------|-------------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 2100 / - | MPa | ISO 527 |
| Strain at break | >50 / - | % | ISO 527 |
| Charpy impact strength, +23°C | N / - | kJ/m ² | ISO 179/1eU |

| Other properties | dry / cond | Unit | Test Standard |
|-------------------------|-------------------|-------------------|----------------------|
| Density | 1110 / - | kg/m ³ | ISO 1183 |

Characteristics**Delivery form**

White

Regional Availability

Europe

Special Characteristics

High impact or impact modified