

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3400	MPa	ISO 527
Yield stress	78	MPa	ISO 527
Yield strain	3.7	%	ISO 527
Strain at break	5.6	%	ISO 527
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	75	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	80	E-6/K	ISO 11359-1/-2
Oxygen index	32	%	ISO 4589-1/-2
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
Other properties			
Density	1160	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Low Odor

Delivery form

Pellets

Regional Availability

Europe

Special Characteristics

Flame retardant