

Product Texts

Polyamide 6, for injection moulding, black

Processing/Physical Characteristics

dry / cond

Unit

Test Standard

ISO Data

^[C] Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Tensile Modulus	3000 / 1000	MPa	ISO 527
Flexural modulus, 23°C	2650 / 850	MPa	ISO 178
Flexural strength	95 / 30	MPa	ISO 178
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / 20	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	170 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	200 / *	°C	ISO 306
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties

dry / cond

Unit

Test Standard

^[C] Density	1140 / -	kg/m ³	ISO 1183
------------------------	----------	-------------------	----------

[C]: CAMPUS

Material specific properties

dry / cond

Unit

Test Standard

ISO Data

Viscosity number	135 / *	cm ³ /g	ISO 307, 1157, 1628
------------------	---------	--------------------	---------------------

Characteristics**Processing**

Injection Molding

Delivery form

Black