

Product Texts

Polyamide 6, improved flowability, for injection moulding

Processing/Physical Characteristics

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.7 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3000 / -	MPa	ISO 527
Flexural modulus, 23°C	2600 / -	MPa	ISO 178
Flexural strength	70 / -	MPa	ISO 178
^[C] Charpy impact strength, +23°C	60 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Electrical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties

	dry / cond	Unit	Test Standard
^[C] Density	1140 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding