

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3000 / 1100	MPa	ISO 527
^[C] Stress at 50% strain	* / 60	MPa	ISO 527
^[C] Stress at break	50 / *	MPa	ISO 527
^[C] Strain at break	15 / >50	%	ISO 527
Flexural modulus, 23°C	2800 / 1000	MPa	ISO 178
Flexural strength	100 / 40	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	4 / 15	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	4 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	60 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1140 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Natural Color