

Product Texts

Heat stabilized grade with good flowability, medium impact resistant and bright natural colour.
For moulding parts with long flow distances and short cycle time.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3100	MPa	ISO 527
Tensile Strength	80	MPa	ISO 527
Yield strain	4	%	ISO 527
Strain at break	20	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	10	%	Sim. to ISO 62
Humidity absorption	3	%	Sim. to ISO 62
Density	1130	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe