

**Product Texts**

Medium viscosity PA6.  
For all kind of parts.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>3100</b>	MPa	ISO 527
Yield stress	<b>80</b>	MPa	ISO 527
Yield strain	<b>3.5</b>	%	ISO 527
Strain at break	<b>15</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>60</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>165</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>9.8</b>	%	Sim. to ISO 62
Humidity absorption	<b>2.7</b>	%	Sim. to ISO 62
Density	<b>1130</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>240 - 270</b>	°C	-

**Characteristics****Regional Availability**

Europe