

Genestar™ N1006A

PA9T

Kuraray Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	50	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy notched impact strength, +23°C	65	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	300	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	125	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	110	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

High impact or impact modified

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa