

Genestar™ G1300A

PA9T-GF30

Kuraray Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	190	MPa	ISO 527
Flexural modulus, 23°C	8800	MPa	ISO 178
Flexural strength	270	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	300	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	125	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	270	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa