

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	6.1 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	2.16 / *	kg	-
Melt flow index, MFI	8.8	g/10min	ISO 1133
Temperature	275	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	20200 / 19900	MPa	ISO 527
Stress at break	230 / 205	MPa	ISO 527
Strain at break	1.6 / 1.6	%	ISO 527
Flexural modulus, 23°C	18800 / 18200	MPa	ISO 178
Flexural strength	338 / 294	MPa	ISO 178
Charpy impact strength, +23°C	50 / 39	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4.4 / 4.5	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	240 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10

Other properties	dry / cond	Unit	Test Standard
Humidity absorption	1.1 / *	%	Sim. to ISO 62
Density	1430 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3	h	-
Mold temperature	120 - 140	°C	-
Zone 1	270	°C	-
Zone 2	275	°C	-
Zone 3	280	°C	-
Nozzle temperature	280	°C	-
Screw speed	60 - 150	rpm	-
Injection pressure	20 - 150	MPa	-

Characteristics

Processing

Injection Molding

Applications

Automotive, Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa