

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17000	MPa	ISO 527
Yield stress	235	MPa	ISO 527
Strain at break	2.1	%	ISO 527
Flexural modulus, 23°C	15000	MPa	ISO 178
Izod impact strength, +23°C	75	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	248	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
ASTM Data			
Melting Temperature	260	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1600	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 12	h	-
Melt temperature	275 - 290	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	250	°C	-
Zone 2	285	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Special Characteristics

High impact or impact modified

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa