

**Product Texts****Microcrystalline and transparent polyamides for for medical application**

**TROGAMID® Care MX** is the material of choice for all applications dealing with pharmaceutical formulations, lipids or aggressive disinfectants, since it exhibits an exceptional resistance towards chemicals and stress-cracking. Examples include fluid and drug delivery equipment such as stop-cocks, dialyzer parts, housings, covers or hearing aids.

Target areas of application for TROGAMID® Care MX compounds include fluid and drug delivery systems, surgical instruments, housings, monitoring and imaging devices and durable medical equipment.

**All advantages at a glance**

- High transparency
- High chemical resistance
- Very good stress crack resistance
- UV resistance
- High dynamic load-bearing capacity
- High impact resistance
- Easy processability & colorability
- Free of BPA
- Gamma and EtO sterilizable

**Biocompatibility of TROGAMID® Care**

Biocompatibility was tested following ISO10993-1 recommendations for a surface medical device with up to 30 days body contact.

The material fulfills the requirements of USP<88> class VI.

Tests were performed by independent, certified laboratories.

**Biocompatibility tests for TROGAMID® Care:****Processing of TROGAMID® Care**

For information about processing of TROGAMID®, please follow the general recommendations about "[Processing of TROGAMID® compounds](#)".

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT [EVONIK-HP@EVONIK.COM](mailto:EVONIK-HP@EVONIK.COM)  
OR VISIT OUR PRODUCT AT [WWW.EVONIK.COM/MEDICAL-TECHNOLOGY](http://WWW.EVONIK.COM/MEDICAL-TECHNOLOGY)

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	8.2 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	280 / *	°C	-
Load	2.16 / *	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.7 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	1400 / -	MPa	ISO 527
<sup>[C]</sup> Yield stress	60 / -	MPa	ISO 527

<sup>[C]</sup> Yield strain	8 / -	%	ISO 527
<sup>[C]</sup> Nominal strain at break	>50 / -	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	14 / -	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Type of failure	C / -	-	-
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / -	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Type of failure	C / -	-	-
<sup>[C]</sup> Shore D hardness	81 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	250 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	140 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	108 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	122 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	130 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	90 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	90 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn. Thickness tested	HB / *	class	IEC 60695-11-10
<sup>[C]</sup> Burning Behav. at thickness h Thickness tested	HB / *	class	IEC 60695-11-10
	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.6 / -	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.2 / -	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	115 / -	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	325 / -	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	27 / -	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	3.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	1.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1020 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion

### Certifications

Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved

**Delivery form**

Pellets

**Applications**

Medical

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather, Transparent, Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Chemical Resistance**

General Chemical Resistance, Environmental Stress Crack Resistance