

CBG7010

(PC+ABS)-GF10

Ever Plastic Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	70.6	MPa	ASTM D 638
Flexural Modulus	2747	MPa	ASTM D 790
Flexural Strength	86.3	MPa	ASTM D 790
Izod Impact notched, 1/8 in	118	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	3	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	80	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific