

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	22000	MPa	ISO 527
Stress at break	265	MPa	ISO 527
Strain at break	1.8	%	ISO 527
Flexural modulus, 23°C	22000	MPa	ISO 178
Izod impact strength, +23°C	50	kJ/m ²	ISO 180/1U

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	15	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1780	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	0.5 - 1.5	h	-
Melt temperature	280	°C	-
Mold temperature	120 - 140	°C	-
Zone 1	250 - 260	°C	-
Zone 2	260 - 290	°C	-
Nozzle temperature	260 - 290	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization, Electron beam (e-beam) sterilization

Features

Creep Resistance

Chemical Resistance

General Chemical Resistance, Radiation Resistance

Certifications

Medical Grade, Biocompatibility ISO 10993, Device Master File

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa