

RamSter PF300J50NT

PBT-(GF+GB)50

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	250	°C	-
Load	5	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.2	%	Producer Method
Molding shrinkage, normal	0.3	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13500	MPa	ISO 527
Tensile Strength	128	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod notched impact strength, +23°C	13.8	kJ/m ²	ISO 180/1A
ASTM Data			
Izod Impact notched, 1/8 in	140	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1720	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.04	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	40 - 60	°C	-
Zone 1	245 - 255	°C	-
Zone 2	245 - 255	°C	-
Zone 3	250 - 260	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa