

ROMILOY® 1035/07 GF10

(PC+ABS)-GF10

Romira GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4250	MPa	ISO 527
Tensile Strength	78	MPa	ISO 527
Strain at break	7	%	ISO 527
Flexural modulus, 23°C	4150	MPa	ISO 178
Flexural strength	111	MPa	ISO 178
Charpy impact strength, +23°C	37	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	26	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	108	°C	ISO 75-1/-2
Vicat softening temperature, B	125	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ISO 1183

Characteristics**Regional Availability**

North America, Europe, Asia Pacific