

RONFALIN® C C130 GF10

(PC+ABS)-GF10

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3800	MPa	ISO 527
[C]: CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	114	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	131	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	130	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.5	class mm	IEC 60695-11-10 -
[C]: CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1200	kg/m ³	ISO 1183
[C]: CAMPUS			

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa