

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	14	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	4200	MPa	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	3	%	ISO 527
Charpy impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	25	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	175	MPa	ISO 2039-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	185	°C	ISO 75-1/-2
Vicat softening temperature, B	195	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Relative permittivity, 100Hz	4.5	-	IEC 62631-2-1
Relative permittivity, 1MHz	4.3	-	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	250	-	IEC 60112
<b>Other properties</b>			
Water absorption	0.35	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1540	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 270	°C	-
Mold temperature	75 - 100	°C	-
Zone 1	250 - 265	°C	-
Nozzle temperature	260 - 270	°C	-
Screw speed	80	rpm	-
Injection pressure	60 - 100	MPa	-
Back pressure	1 - 3	MPa	-
Holding pressure	40 - 80	MPa	-
Maximum residence time	10	min	-

**Characteristics**

**Processing**

Injection Molding

**Features**

Low Warpage

**Delivery form**

Pellets, Natural Color

**Regional Availability**

Europe

**Special Characteristics**

Heat stabilized or stable to heat