

RamSter PF340S6NT

PBT-GB30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4000	MPa	ISO 527
Tensile Strength	46	MPa	ISO 527
Strain at break	5.4	%	ISO 527
Izod notched impact strength, +23°C	3.5	kJ/m ²	ISO 180/1A

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.04	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	40 - 60	°C	-
Zone 1	245 - 255	°C	-
Zone 2	245 - 255	°C	-
Zone 3	250 - 260	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa