

**QR Resin QR-1200-GF16**

(PC+ABS)-GF16

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>82.7</b>	MPa	ASTM D 638
Flexural Modulus	<b>5000</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>76</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>121</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1260</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>82 - 121</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>232 - 288</b>	°C	-
Mold temperature	<b>43 - 82</b>	°C	-
Zone 1	<b>232 - 260</b>	°C	-
Zone 2	<b>232 - 288</b>	°C	-
Zone 3	<b>232 - 288</b>	°C	-
Nozzle temperature	<b>232 - 288</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

General Purpose

**Regional Availability**

North America