

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® SK602 NC010 is a 15% glass fiber reinforced, lubricated polybutylene terephthalate resin for injection molding.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
^[C] Density of melt	1220	kg/m ³	-
^[C] Thermal conductivity of melt	0.24	W/(m K)	-
^[C] Spec. heat capacity of melt	1900	J/(kg K)	-
^[C] Ejection temperature	170	°C	-
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.012	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5800	MPa	ISO 527
^[C] Stress at break	109	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527
^[C] Tensile creep modulus, 1h	5300	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	4300	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	45	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	6000	MPa	ASTM D 638
Tensile Strength	100	MPa	ASTM D 638
Elongation at Break	3.6	%	ASTM D 638
Flexural Modulus	5976	MPa	ASTM D 790
Flexural Strength	160	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	58	J/m	ASTM D 256
Temperature	-40	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	55	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2

Crastin® SK602 NC010

PBT-GF15

Celanese

[C] Vicat softening temperature, B	205	°C	ISO 306
[C] Coeff. of linear therm. expansion, parallel	50	E-6/K	ISO 11359-1/-2
[C] Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
[C] Burning rate, FMVSS, Thickness 1 mm	30	mm/min	ISO 3795 (FMVSS 302)
[C] Oxygen index	19	%	ISO 4589-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Coefficient of Thermal Expansion, MD	50	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	110	E-6/K	ASTM D 696
DTUL @ 66 psi	220	°C	ASTM D 648
DTUL @ 264 psi	195	°C	ASTM D 648

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
[C] Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
[C] Relative permittivity, 1MHz	3.5	-	IEC 62631-2-1
[C] Dissipation factor, 100Hz	7	E-4	IEC 62631-2-1
[C] Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
[C] Surface resistivity	1E15	Ohm	IEC 62631-3-2
[C] Electric strength	27	kV/mm	IEC 60243-1
[C] Comparative tracking index	350	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	23	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Dielectric Constant, 1 MHz	3.5	-	ASTM D 150
Surface Resistivity	1E15	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Water absorption	0.42	%	Sim. to ISO 62
[C] Humidity absorption	0.17	%	Sim. to ISO 62
[C] Density	1410	kg/m ³	ISO 1183
Density	1410	kg/m ³	ASTM D 792

[C]: CAMPUS

Material specific properties	Value	Unit	Test Standard
ISO Data			
[C] Viscosity number	105	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Chemical Resistance

General Chemical Resistance

Crastin® SK602 NC010

PBT-GF15

Celanese

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Features

Weldable

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa