

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	6000	MPa	ISO 527
Stress at break	75	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Charpy impact strength, +23°C	55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	7	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	200	°C	ISO 75-1/-2
Vicat softening temperature, B	190	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.6	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112
<b>Other properties</b>			
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1530	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Special Characteristics

Flame retardant, High impact or impact modified, U.V. stabilized or stable to weather

### Features

Thermal Stability

### Chemical Resistance

General Chemical Resistance

### Applications

Electrical and Electronical

### Regional Availability

Europe