

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	74	MPa	ASTM D 638
Flexural Modulus	5592	MPa	ASTM D 790
Flexural Strength	128	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	57	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	40	E-6/K	ASTM D 696
DTUL @ 66 psi	222	°C	ASTM D 648
DTUL @ 264 psi	204	°C	ASTM D 648
Melting Temperature	224	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	26	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	3.5	-	ASTM D 150
Arc Resistance	120	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.08	%	ASTM D 570
Density	1430	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Special Characteristics

Flame retardant

### Regional Availability

North America, Asia Pacific