

**SPESIN® KP213G15HIBL**

PBT-GF15

Kolon Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.009</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	<b>88</b>	MPa	ASTM D 638
Flexural Modulus	<b>4413</b>	MPa	ASTM D 790
Flexural Strength	<b>147</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 113</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>118</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.8</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>50</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>155</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>60</b>	°C	ASTM D 648
Melting Temperature	<b>224</b>	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>26</b>	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	<b>3.6</b>	-	ASTM D 150
Arc Resistance	<b>130</b>	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	<b>0.05</b>	%	ASTM D 570
Density	<b>1370</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Black

**Regional Availability**

North America, Asia Pacific

**Special Characteristics**

High impact or impact modified