

TORAYCON® 1101G-X53

PBT-GF15...

Toray Industries, Inc.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	97	MPa	ISO 527
Strain at break	2.7	%	ISO 527
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ISO 1183

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa