

**Product Texts**

Injection Molding, 25% Glass Reinforced, Flame Retardant (halogen free), Recycled Content

ISO 1043 PBT-GF25 FR(40+30)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	40	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.2	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10000	MPa	ISO 527
<sup>[C]</sup> Stress at break	100	MPa	ISO 527
<sup>[C]</sup> Strain at break	2	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	35	kJ/m <sup>2</sup>	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	224	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
<sup>[C]</sup> Burning Behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.5	mm	-
<sup>[C]</sup> Oxygen index	43.7	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.7	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	40	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	140	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	35	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	575	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.5	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.1	%	Sim. to ISO 62
<sup>[C]</sup> Density	1520	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Flame retardant, Halogen-free

**Certifications**

Recycled Resin Content

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information**

**Injection molding**

**PREPROCESSING**

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 120 °C

Drying time circulating air dryer: 4 - 8 h

**PROCESSING**

Melt temperature (Tmin - Tmax): 250 - 270 °C

admissible residence time at Tmax: <5 min

Mold temperature: 70 - 90 °C