

4DUR 9K22130 XHFR1

PBT-GF30

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	11000	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod impact strength, +23°C	65	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	9 -30	kJ/m ² °C	ISO 180/1A -
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.0	mm	-
Electrical properties			
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	225	-	IEC 60112
Other properties			
Density	1650	kg/m ³	ISO 1183
Moisture Content	0.08	%	-

Characteristics**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

Regional Availability

Europe